

Recent Developments of LS-DYNA® in Stamping Simulation

Xinhai Zhu

November, 2009



LSTC
Livermore Software
Technology Corp.

8/3,4/09

Outline

- ◆ Implicit method
- ◆ Material work-hardening
- ◆ Some new keywords
- ◆ Surface low detections
- ◆ Conclusions



Improvements in Implicit Method



Livermore Software Technology Corporation

Implicit Method

◆ Implicit method has been gaining more popularities in sheet stamping simulation

- Initial application was mainly limited to springback predictions
- Gravity loading simulation has been proven to be robust with implicit method
- Implicit method has also shown great potentials in flanging simulation.



Implicit Method: Binder Wrapping

◆ Binder wrapping characteristics

- Large blank movements, large dynamic effect
- Small plastic deformation
- Element is relatively coarse, and the number of element is small
- Implicit method might be the preferred one


◆ Recent developments

- New implicit contact
- New features to help convergence
- An extensive parameter studies
 - ◆ The default parameters are suitable for most of the binder wrapping process
 - ◆ It is easy to use
 - ◆ User in-dependent results can be obtained




Implicit Method: Binder Wrapping

- ◆ The proper step size for a typical binder wrapping process
 - The new algorithm allow large time step. While the old time will limit the time step size
 - Too small time step will require many time steps
 - Too large time step will require more iterations, sometimes, the result is not good




Implicit Method: Binder Wrapping

- ◆ Too small time step might have convergence problem



Implicit Method: Binder Wrapping



- ◆ Reasonable time step should make sure that most of the rigid body motions are constrained



Implicit Method: Binder Wrapping


◆ A typical time step selection

- 10 time steps are used
- It took 12 minutes to finish with ONE CPU




Implicit Method: Binder Wrapping

- ◆ Binder and Gravity Loading are combined into one simulation
 - In the old method, gravity loading has to be done separately
 - It allow mesh refinement during each step
 - It allows guide pins




Implicit Method: Binder Wrapping

- ◆ After Gravity Loading, blank elements are refined



Implicit Method: Binder Wrapping

- ◆ Final geometry: all the buckling mode has been correctly simulated
 - It took 90 minutes to finish



Implicit Method: Other Applications

- ◆ Initially developed for metal stamping simulations that involve gravity loading of blanks on dies.
- ◆ Now extended as a general capability
 - Serial, SMP and MPP implementation
- ◆ Robust contact treatment
- ◆ Vehicle does not need to be supported to eliminate rigid body modes
- ◆ Elimination of loose parts not required
- ◆ Reduces model preparation time dramatically over traditional implicit method.



Implicit Method

Compensation Based on Scan Data

- ◆ Sometimes, springback predictions are not accurate
 - Scan data can be used to compensate the springback deviations
- ◆ Procedure in using scan data
 - Perform a forming simulation, and obtained the deformed part
 - Assume the scan data as rigid tools
 - Assume the deformed as a deformable
 - Apply internal pressure to the deformed part
 - After push, the blank geometry can be used as sprung shape
 - Use the same procedure as before and compensate the rigid



Implicit Method Compensation Based on Scan Data


- ◆ How to push the deformed part to the scanned geometry?
 - The pressure is applied by using load mask
 - ◆ All the blank element will have a normal pressure
 - ◆ The pressure is applied to the opposite of element normal directions
 - Blank normal has to be checked
 - ◆ For most of the situation, the internal pressure can be in the range of 20 ~ 30 MPA
 - Use implicit method
 - ◆ Use the keyword: *CONTROL_IMPLICIT_FORMING
 - ◆ One step pushing is used
 - ◆ The CPU time is small (usually can be done within a few minutes)



Implicit Method Compensation Based on Scan Data


◆ Benchmark Study:

- Number of element: 41,457
- CPU cost: 7 minutes and 39 seconds



Implicit Method Compensation Based on Scan Data

- ◆ Problems might happen during the pushing:
 - No support for the boundary elements



Over-bend in the boundary areas



Implicit Method

Compensation Based on Scan Data

- ◆ Change the boundary elements to a different part
 - Avoid applying pressure to the boundary element



Implicit Method

Compensation Based on Scan Data


- ◆ After first tryout, the parts exhibited significant springback issues.
- ◆ Part could not even be placed on the checking fixture without extreme hand-working.
- ◆ Part was bowed throughout the length of the channel, twisted, there were bulges adjacent to the deeper areas of form, form depth in the deeper areas was incorrect, and the stepped flanges were crowning.
- ◆ Part showed that it was under-bent just about everywhere.



Implicit Method Compensation Based on Scan Data

◆ Example:

- ◆ There is a dramatic change.
- ◆ A significant amount of springback has been removed
- ◆ With adjustments to magnification, an even more effective compensated shape could have been created.



Material kinematic hardening

Yoshida model

Chaboche's model



Springback Prediction for HSS

- ◆ Some parts are sensitive to stress noise
 - More accurate stress calculation is important



Twisting mode corresponding to the lowest frequency (17.97)


And is far smaller than the next one: 54.7

Accordingly, small stress noise might excite the wrong twisting mode



Yoshida Kinematic Hardening

- ◆ Recent researches found that Yoshida non-linear kinematic hardening is the preferred one.
 - It can describe the softening effect from reverse loading
 - It can accurately represent the stress-strain curve from the cyclic load



Reference: Yoshida's paper: J. of Mech. Sci. Vol. 45, p. 1687

Yoshida Kinematic Hardening

◆ Key points of Yoshida's theory:

- Yield surface does not change in size
- Center of yield surface moves with deformation
- Bounding surface change both in size and location

$$\alpha_* = \alpha - \beta.$$

$$\dot{\alpha}_* = C \left[\left(\frac{a}{Y} \right) (\sigma - \alpha) - \sqrt{\frac{a}{\bar{\alpha}_*}} \alpha_* \right] \dot{p},$$

$$\dot{p} = \sqrt{(2/3) \mathbf{D}^P : \mathbf{D}^P}, \quad \bar{\alpha}_* = \phi(\alpha_*), \quad a = B + R - Y,$$




Fig. 2. Schematic illustration of the two-surface model

Yoshida Kinematic Hardening

- ◆ Bounding surface changes in both its size and location:

$$\dot{R} = k(R_{sat} - R)\dot{p},$$

$$\dot{\beta}' = k \left(\frac{2}{3} b \mathbf{D}^P - \beta' \dot{p} \right)$$

$$\sigma_{bound} = B + R + \beta = B + (R_{sat} + b)(1 - e^{-k\varepsilon^P}).$$




Yoshida Kinematic Hardening

◆ Work-hardening stagnation

$$g_{\sigma}(\boldsymbol{\sigma}', \mathbf{q}', r') = \frac{3}{2}(\boldsymbol{\sigma}' - \mathbf{q}') : (\boldsymbol{\sigma}' - \mathbf{q}') - r'^2 = 0,$$

$$\overset{\circ}{\mathbf{q}}' = \mu(\boldsymbol{\beta}' - \mathbf{q}').$$

$$\dot{r} = h\Gamma, \quad \Gamma = \frac{3(\boldsymbol{\beta}' - \mathbf{q}') : \boldsymbol{\beta}'}{2r}$$






Material Data Fitting Comparisons (DP600)



Material Parameters


$Y = 0.253E+03$
 $m = 0.405E+02$
 $B = 0.342E+03$
 $h = 0.100E+01$
 $c = 0.430E+03$
 $b = 0.155E+03$
 $rsat = 0.543E+03$



The obtained parameters can nicely represent the stress-strain curves in different loading paths.

Yoshida's Model Characteristics

- ◆ Yoshida's Model can give good fit of the test
 - The effective strain usually small (<0.16)
- ◆ Yoshida Model shows saturation of stress



Chaboche's Model (M103)

◆ Difficulty in using it

- There are eight user-defined material variables, make it difficult for ordinary user to use it
- The build-in curve fitting only works for one stress-strain curve
 - ◆ Uniaxial-tension curve has to be used
 - ◆ It is impossible to get an reasonable material parameters




◆ An optimization algorithm has been developed

- It is a stand-alone code
- Up to eight stress-strain curves can be used as input
 - ◆ The file names should begin from curve1.inc, curve2.inc...
- Many iterations will be needed

$$\bar{\sigma} = \sigma_0 + Q_{r1}(1. - \exp(-C_{r1}\bar{\epsilon})) + Q_{r2}(1. - \exp(-C_{r2}\bar{\epsilon})) + Q_{x1}(1. - \exp(-C_{x1}\bar{\epsilon})) + Q_{x2}(1. - \exp(-C_{x2}\bar{\epsilon}))$$



Chaboche' Mixed-Hardening Model DP600




Livermore Software
Technology Corp.

Livermore Software Technology Corporation

Chaboche' Mixed-Hardening Model Saturation problem

◆ Chaboche's Model has saturation problem

- The stress strain curve is extended by power law
- Then fit the curve and obtain the parameters
- The fitted curve does not match the experimental data



Modifications of Yoshida's Model


New Proposal

- ◆ A new algorithm has been proposed and tested
 - Use a power-law to replace the R calculation in Yoshida's model
 - The old function: $\dot{R} = k(R_{sat} - R)\dot{p}$,
 - The new function: $R = R_{sat}(e + e_0)^{-n} - R_{sat}(e_0)^{-n}$
 - This new function will not have saturation problem
 - There are two more parameters need to be fit: e_0 and n



Modifications of Yoshida's Model


Example: DP600



The stress-strain curve was extended by a power law
Original strain range is: 0~0.15
The fitted parameter: $k=950$, $n = 0.16$


Modifications of Yoshida's Model

Example: DP600



MODIFICATIONS OF YOSHIDA'S MODEL

Example: DP600



Some New Keywords

important for line-die simulation



Coordinate-based constraint

❖ Why we need to put constraints on coordinates

- It can be more accurate to constraint the model in a fixture
- It can automate line-die simulation

❖ The keyword is

- *CONSTRAINED_COORDINATE
- It can also be applied to local coordinate system
- Coordinates can be obtained from stationary tool in the CASE before springback.



```
*constrained_coordinate
```

```
$---+---1---+---2---+---3---+---4---+---5---+---6---+---7---+---
```

```
8
```


```
$ ID IDPT IDIR(DOF) x y z CID
```

```
$ unique ID, PartID, DOF (one at a time)
```


1	1	3	1326.28	-100.236	156.434
2	1	3	1276.21	159.983	138.517
3	1	3	2466.03	-100.241	156.464
4	1	3	2516.35	151.889	138.81
5	1	1	2454.17	121.142	135.007
6	1	2	2454.17	121.142	135.007
7	1	2	1339.84	118.347	135.237

Line Die Simulation


NUMISHEET Fender on Air with Flanging - Flanging



line = 0.1609, #nodes=447805, #elem=439392
Contours of Pressure
hull integration p0r1
min=-350.584, at elem# 1767942
max=285.406, at elem# 1777715



Fringe Levels
2.100e+02
1.450e+02
9.000e+01
5.000e+01
0.000e+00
-1.150e+02
-1.800e+02
-2.450e+02
-3.100e+02




Flanging simulation progression



Livermore Software Technology Corporation

Line Die Simulation



NUMISHEET Fender on Air with Multi-flanging – Flanging in Three Areas




Line Die Simulation

NUMISHEET Fender on Air with Multi-flanging – Details

Hood line flanging



New Option for Trimming



Define a seed node on stationary tool (not blank) for trimming; use negative option


```
*node
105226,2026.19,292.148,-134.788
*DEFINE_CURVE_TRIM_NEW
$#  tcid  tctype  tflg  tdir  tctol  toln  nseed
      1    2      0     0    0.250      -105226
deck_trimline.iges
```

Or,

```
*DEFINE_CURVE_TRIM_NEW
$#  tcid  tctype  tflg  tdir  tctol  toln  nseed
      1    2          0    0.250
deck_trimline.iges
*define_trim_seed_point_coordinates
$  NSEED      X1      Y1      Z1      X2      Y2
Z2
1  2026.19 292.148 -134.788
```




Surface Defect (Surface Low) Prediction



Livermore Software Technology Corporation

Reflect light on a stamped panel

Surface Defect (Surface Low) Prediction





- Smoothed surface for stoning and curvature calculation
- Stoning direction can be manually defined by two nodes, or input # of directions without Node1 and Node2 definition



Surface Defect (Surface Low) Prediction

◆ Stoning method – no mesh refinement

- 2.0mm element size around door handle untrimmed – one way curvature.
- Mesh built with surface (not splitting from a coarser mesh)
- Results are in the order of 1.0E-04 to 1.0E-05.



Summary:

Basically no differentiation in surface lows.



Livermore Software Technology Corporation


*CONTROL_FORMING_STONING

\$	ISTONE	LENGTH	WIDTH	STEP
	1	150.0	4.0	1.00
\$	NODE1	NODE2	SID	ITYPE
	,,1,2			

DIRECT	REVERSE	METHOD
2	0	0

Surface Defect (Surface Low) Prediction

◆ Stoning method



Summary:

Expected.



Livermore Software Technology Corporation

*CONTROL_FORMING_STONING

\$	ISTONE	LENGTH	WIDTH	STEP
	1	300.0	4.0	0.10

\$	NODE1	NODE2	SID	ITYPE

\$ stone orientation in all direction

,,1,2



DIRECT
8

REVERSE
0

METHOD
0

Surface Defect (Surface Low) Prediction

◆ Stoning method



Summary:


Expected.



Livermore Software Technology Corporation



*CONTROL_FORMING_STONING

\$	ISTONE	LENGTH	WIDTH	STEP	DIRECT	REVERSE	METHOD
	1	300.0	4.0	0.10	8	0	0
\$	NODE1	NODE2	SID	ITYPE			
\$ stone orientation in all direction							
,,1,2							



Surface Defect (Surface Low) Prediction

◆ Stoning method



Summary:


Expected.



Livermore Software Technology Corporation



*CONTROL_FORMING_STONING

\$	ISTONE	LENGTH	WIDTH	STEP	DIRECT	REVERSE	METHOD
\$	1	150.0	4.0	1.00	2	0	0
\$	NODE1	NODE2	SID	ITYPE			
	,,1,2						



Surface Defect (Surface Low) Prediction

◆ Curvature method



Summary:


Captures the boundary of the surface low area. Inside of the boundary no curvature change. Expected.



Livermore Software Technology Corporation

*CONTROL FORMING STONING

\$	ISTONE	LENGTH	WIDTH	STEP
	1	150.0	4.0	1.00
\$	NODE1	NODE2	SID	ITYPE
\$ stone orientation in all direction				
				,,1,2



Conclusions

- ◆ LSDYNA's Implicit capability becomes even more robust and efficient
- ◆ LSDYNA can continue maintains technical leader in sheet stamping simulation

